

IDEAL CHLORINATED RUBBER PAINT

PRODUCT DESCRIPTION AND USES

Ideal Chlorinated Rubber paint is a hard-wearing chemical resistant paint for use in areas where high chemical resistance is required e.g. in chemical factories, marine vessels, dairy industry, breweries etc.

Ideal Chlorinated Rubber paint can be applied on plaster, cement, steel, concrete and wooden surfaces. It is resistant to mild acids and alkalis.

Recommended for use on swimming pools.

SURFACE PREPARATION

Iron and steel

Prime the metal with 1 coat of Ideal Zinc Phosphate or Ideal Zinc Chromate Primer. On galvanized iron and iron ferrous metals - Prime with 1 coat of Ideal Etch Primer

On plaster and wood

Prime with 1 coat of Ideal Etch Primer. Finish with 2-3 coats of Ideal Chlorinated Rubber paint.

FINISH

Gloss

APPLICATION

By brush or spray

THINNING AND MIXING

Ideal Chlorinated Rubber thinner – 1 part thinner to 4 parts paint

EQUIPMENT CLEANING

Clean equipment immediately after use with Ideal Chlorinated Rubber thinner.

DRYING TIME

6 hours

COLOUR RANGE

White

SPREADING CAPACITY

9-11 M² per litre at 40 microns DFT

PACK SIZES

4 litres & 20 litres.